

TECHNICAL NOTES

BARRIER FOIL LOCKING BAGS AND POUCHES

Product No. 139-310, 139-311, 139-312, 139-313



Description:

- Shown above with our Specimen Storage these barrier bags are ideal for storage of materials sensitive to moisture and/or oxygen. The inside dimensions measure L x H x W (where W is the pouch bottom
- width) with a locking and a tear notch above the locking sealer. The material is a metal foil-covered
- 4mil polyethylene with a MVTR (moisture vapor transmission rate) that is 1,000 times better than a typical poly bag. They are heat sealable, and locking resealable. Compatible with vacuum sealers.
- Sizes to fit all your needs.

Applications:

- Barrier foil bags are a cost-effective storage solution used where very low oxygen and moisture levels are required. The material is FDA approved and has a shiny silver appearance. It is used extensively in
- food, medical, and general industry. Bags can be used with desiccants to enhance storage.
- Typical applications Include:
 - Storage of moisture and oxygen sensitive materials/samples
 - Storage of Light sensitive materials/samples
 - Storage of Immunofluorescence labeled, Confocal or Immunology ANA slides from room temperature to freezer
 - Storage of radioactive labeled electrophoresis gels for both refrigerator and freezer
 - Storage and transport of gas monitor badges
 - 139-310, 139-311, 139-312, 139-313 TN V2 10042021

Page 1 of 2




Products Offered:

139-310, Barrier Foil locking Bag, 6 x 5.5" ID	pkg/100
139-311, Barrier Foil locking Pouch Small, 3.75 x 6 x 2.5" ID	pkg/100
139-312, Barrier Foil locking Pouch Medium, 6.25 x 7.75 x 2.5" ID	pkg/100
139-313, Barrier Foil locking Pouch Large, 7.5 x 8.75 x 3" ID	pkg/100

Physical Description:

Laminated PET/Aluminum Foil/Poly barrier bag with locking and heat sealable closure.



Physical Properties:

PROPERTIES	TEST METHOD	UNIT OF MEASURE	TYPICAL VALUE
Caliper		mils	4.0
MVTR	Mocon	gms/100 sq. in./24 hrs	.0006
OTR	Mocon	cc/100 sq. in./24 hrs	.0006
Burst	Mullen	psi	58
Tensile MD	ASTM D-882	lbs. at break	21
Tensile XMD	ASTM D-882	lbs. at break	22
Tear MD	ASTM 689	lbs. at break	96
Tear XMD	ASTM 689	lbs. at break	96
Puncture	Fed. TM 2065	lbs.	13

Comparison Moisture Barrier & Oxygen Barrier Transmission Rates for Other Common Plastic films

FILM	MOISTURE BARRIER	OXYGEN BARRIER			
	MVTR	OTR			
	gm/mil/100 sq. in./24 hrs.	cc/mil/100 sq. in./24 hrs.			
	at 100° F & 90% RH	at 23° C			
Low Density Polyethylene LDPE	1.0 -1.5	350			
High Density Polyethylene HDPE	0.3 - 0.4	150			
Polypropylene PP	0.25	150			
Polyethylene Terephthalate PET	1.0 - 1.3	3-4			
Polystyrene PS	7.0-10.0	350			
Poly Vinylidene Chloride (Saran)	0.10	0.05- 0.15			
PVDC	0.10	0.05- 0.15			
Poly Vinyl Chloride PVC	0.9 - 5.1	5-20			

The values indicated in this document are the results of tests made in compliance with the normal standards. They are given as an indication and should be considered as average values and given without any obligation on our part. This data was provided directly to Ted Pella Inc. from our film supplier.

139-310, 139-311, 139-312, 139-313 TN V2 10042012

TED PELLA. INC.

Microscopy Products for Science and Industry